

TECHNICAL SHEET

DELKOLOR – PEINTURE EFFET MARTELE



CLASSIFICATION

Nitrosynthetic paint quick drying, easy to use, applicable on metal, cars, motorcycle, bicycle etc.

DESCRIPTION

BINDER TYPE

Nitrosynthetic

COLOUR

Azur, Grey, Silver

VISCOSITY

12" F4 at 20 °C

CAN PRESSURE

From 4.2 to 4.8 Bar at 20 °C
From 7.6 to 8.4 Bar at 50 °C

DRYING TIME

08 min
into air at 20 °C
20 min

15 hrs

| | |
|-----------|------|
| Dust free | 05 ÷ |
| Touch dry | 15 ÷ |
| Total | 10 ÷ |

GLOSS LEVEL

72/76 Gloss

SPREADING CAPACITY

From 0.9 to 1.1 m² for a 400 ml can.

STORAGE

Fresh and ventilated place.

APPLICATION

BEFORE USE READ CAREFULLY THE INSTRUCTIONS UPON THE CAN!

The surface of application must be perfectly clean, dry, degreased, and free from rust particles and in case treated with anti-rust. Before use shake well the can at last two minutes. Spraying covering layers at a distance of 25 cm, in one coat.

N.B.

The above information covers at best our knowledge, but are not vinculating.

THE LABORATORY/SGQ



NOVODIS
4 Avenue Antoine Becquerel – ZI Bersol – 33600 PESSAC
France
T +33 557 266 600 - F +33 557 266 633
commercial@novodis.fr - www.novodis.fr